187966 SLIM GOLD

10mm 0,8x90 cm./0.3x35.4in. • D153

Información Técnica / Technical Information

Icono	Prueba	Norma	Resultado
, ↓	DIMENSIONS	UNE EN ISO 10545-2	± 0,5%
٥	WATER ABSORPTION	UNE EN ISO 10545-3	E <= 0.5%
Д	CHEMICAL RESISTANCE	UNE EN ISO 10545-13	GLB
*	RESISTANCE TO STAINS	UNE EN ISO 10545-14	4

Embalaje / Packing						
[m ²]		- Kg	Lbs	_	 	M ²
138.89	6	0.6	1.32	2592	0.04	111.97

Uso	s / Use	es							
→	ţ	F	ţ	9999 9999					
NO	NO	\checkmark	NO	NO	NO	NO	NO	NO	NO

C = CONSULTAR / CONSULT

Características



Shade variation

lcono embalaje







SATIN



M2/caja

Satinado

Satin finish

Piezas/caja

Pieces/box



Kg

|||| ∅/



Kg/caja

Kg/box

Graphic variation

Variación gráfica

Producto delicado * Delicate



Libras/caja Lbs Lbs/box



lconos usos



Outdoor floors Outdoor floors



Indoor walls Indoor walls

Indoor floors Indoor floors



Commercial flooring Commercial flooring



Underfloor heating installation Underfloor heating installation







(depth>1,5m) Swimming pool. Wall and floor (depth>1.5m)



Walls high vapor condensation areas Walls high vapor condensation areas

ATTENTION

Carefully follow these instructions to ensure correct installation.

- Installation should be carried out by a qualified professional.
- Before installing ensure that the material is in perfect condition. Make sure you check the colours, finishes and thicknesses because DUNE will not accept any claims or returns of material after it has been installed.
- Before each stage, on one part test all of the materials and tools to be used and evaluate the final finish of the test. Should you fail to achieve the desired results do not continue with the installation, and consult our sales team.
- In public places materials must comply with the slipperiness requirements of the Spanish Technical Building Code.
- This document is purely commercial and may not be used in any legal or administrative proceedings, neither as an expert opinion nor as documentary evidence, unless expressly authorized by DUNE CERÁMICA S.L.

FLOOR AND WALL TILES – METAL

1. PROPER PREPARATION OF SURFACE

The wall must be firm, levelled, dry and clean. Uneven surfaces greater than 2 mm must be levelled with specific products. All cracks and imperfections should be repaired, so that the wall is completely smooth. The moisture content of the surface must be under 2%.

2. INSTALLATION MATERIAL

For a correct installation, several factors must be taken into account: Material kind of the wall to be tiled (synthetic pannels, plaster, wood, etc.), wall stability, environmental conditions, kind of surface to be covered, speed of carrying the work, etc. All the above parameters determine the choice of the adhesive kind.

All the adhesive materials recommended by DUNE have been previously tested in our facilities, in controlled environmental conditions and on rigid brick and/or concrete walls. Under different conditions from the above mentioned, it is recommended to test firstly and if in doubt, please contact DUNE or the adhesive distributor.

Use C1 cement based, C2 cement based, or epoxy based adhesives. Do not apply too much of this material and always follow the adhesive manufacturer's instructions.

DUNE always recommends to test first the material with minimum two pieces before placing all the material.

3. INSTALLATION

We recommend starting the installation from the floor to the ceiling, continue in phase to allow the adhesive the necessary time to get dry. Extend a thin layer of adhesive on to the surface where the piece will be installed (3mm approx.) Then, use a notched trowel no. 3 to make incisions into the adhesive layer. Place the piece while the adhesive is still soft and before a dry layer of film forms on the adhesive surface. Once the piece is placed, press carefully to obtain correct adhesion and cover possible areas without adhesive.

For a better fixing, it is recommended to set the pieces by using some tape or a wooden strip. To correct the position of the bases, it is recommended to take them off and correctly clean their back part before placing them again. We recommend a minimum joint of 2mm and the use of crosspieces.

For areas with severe thermal dilatation or non-stable surfaces (plasterboard), a minimum joint of 3 mm is strongly recommended.

4. GROUTING

All joints must be perfectly clean and dry and having a minimum depth of 2mm. Use a flat rubber trowel to spread the paste, being sure that the joints are completely covered. Use a wet sponge or neutral PH products – never abrasive products – to wash off immediately the excess of grouting paste from the surface before it dries. If this happens, use a cement remover to clean the surface

For better waterproofing, we recommend an epoxy grouting paste, especially in water areas

Consult the grouting materials table.

Important:The colour of the grouting paste might change the product's appearance. We recommend to test with some pieces before grouting the entire surface.

5. CLEANING AND MAINTENANCE

For everyday cleaning, use regular cleaners con PH neutro. Do not use abrasive products.

Tabla de adhesivos / Adhesives Table				
	Cemento cola C1	Cemento cola C2	Adhesivo epoxidico	
	C1 concrete glue	C2 concrete glue	Epozi adhesive	
KERAKOLL	ESPECIAL ECO	H 40 ECO FLEX	SUPERFLEX ECO	
MAPEI	TIXOBOND	KERAFLEX MAXI S-1	KERALASTIC T	
	Mortero adhesivo látex Latex adhesive mortar			
LATICRETE	Mortar 211 + Laticrete 4237			

Productos de tratamiento / Tratment products				
	Código	Descripción	Código PHP recomendado	
	Code	Description	Recommended retail price	
CRISTAL GLASS	185463	ANTIGLISS	D787	
PIEDRA	184507	CERA LIQUIDA PROTECTORA LIQUID PROTECTIVE WAX	D945	
STONE	184508	SELLADOR ANTIMANCHAS STAIN-PROF SEALER	D969	

Tabla de pastas de rejuntar / Grouting pastes table				
	Pasta de rejuntar cementosa	Pasta de rejuntar epoxi		
	Cement grouting material	Epoxy grouting material		
KERAKOLL	FUGABELLA ECO PORCELANA	FUGALITE		
MAPEI	KERACOLOR FF	KERAPOXY		
LATICRETE	LATICCRETE serie 1600	-		

